


Fermacell 2E32

Floorboards with mineral wool



Fermacell's flooring panel system is designed to be used as a floating subfloor for a wide variety of applications. Made from 100% recycled cellulose fibers and synthetic gypsum, this effective soundproofing system offers a dry, sturdy and simple solution for all your flooring needs.

Fermacell's 2E32 floorboards are composed of two fiber-gypsum panels (2x10mm) in addition to a laminated layer of mineral wool (10mm). The two panels are offset from one another, so that there is a 50mm wide protrusion, allowing for a stable and solid assembly. The panel dimensions are 1500mm x 500mm (giving an area of 0.75m²).



Advantages

- CCMC evaluation
- Better acoustic isolation
- Low weight and quick installation
- Compatible with all floor coverings
- Can be used rapidly after installation
- Eco-friendly

*For more information, do not hesitate to visit our website or to contact us directly.


 www.dccsolutions.ca

 info@dccsolutions.ca

 418-834-2171

Fermacell

Technical sheet - Characteristics

Fermacell 2E32 material characteristics	
Thickness of the full element	30mm
Weight of the full element	18,6 kg (41 lbs)
Nominal weight	24,7 kg/m ² / (5.06 lbs/ft ²)
Thermic resistance	0,31 m ² *K/W
Fermacell gypsum fiber boards characteristics	
Density	1150 ± 50 kg/m ³
Resistance coefficient to water evaporation diffusion	μ = 13
Thermal conductivity coefficient	λ = 0,32 W/mK
Specific thermic capacity	c = 1,1 kJ/kgK
Brinell Hardness	30 N/mm ²
Thermic dilation coefficient	0,001 %/K
Swelling/Shrinkage in the event of a 30% relative humidity change (at 20°C)	0,25 mm/m ²
Equilibrium rate in relation to the atmospheric air at 65% humidity and 20°C	1,3 %
pH	7 - 8
Fermacell's 14136-R CCMC evaluation report results *	
	
Robinson test (ASTM 627)	Pass
Resistance to fungus (ASTM D3273)	Pass
Resistance to hard impact (ASTM E661-03)	Pass
Resistance to soft impact (ASTM E661-03)	Pass
Data for resellers	
Item number	76030
Quantity/pallet	30 panels
Yield/pallet	22,5m ² /242,1ft ²
Weight/pallet	590 kg/1300 lbs

* Evaluation report done on a Fermacell 2E11 panel