

Technical data sheet

Finitec Synergy

PHYSICAL PROPERTIES

Color	Translucent amber
Solid content (w/w)	30 % ± 2 %
pH	7,6 ± 0,4
Resistance to chemicals	Excellent
Resistance to abrasion (Taber test)	Mass loss: 25 mg (1000 revolutions - ASTM D-4060)
VOC	275 g/L *NMP free (N-Methyl-2-pyrrolidone)
Flash point	N. A.
Luster 60°	Gloss: 90 % - Semi-gloss: 60 % - Satin: 25 %
Freeze / thaw stability	Keep from freezing
Drying time (depending on conditions)	To touch: 1 hour
	To recoat: 4 to 5 hours
	Light traffic: 5 hours
	Furniture: 24 hours
	Carpets and rugs: 7 days
Complete cure: 7 days	
Viscosity	23 to 25 seconds (Zahn #2)
Density	1,03 - 1,05 kg/L

TECHNICAL DATA

Coverage	165 sq.ft. (15,3 m ²) / liter (depending on conditions)
Available sizes	3,64 L
Shelflife	12 months (when kept in its original container)
Tools	Finitec applicator, T-bar, brush or 3/8" (10 mm) roller
Tools clean-up	Water
Storage	Between 10 and 30 °C (50 and 85 °F)
Waste disposal	Recycle if possible (Consult local authorities)

FIRST AID AND WARNING

In case of eye or skin contact, rinse well with water for 15 minutes. In case of inhalation, allow the victim to rest in a well-ventilated area. If swallowed, seek medical attention. Do not induce vomiting. Have conscious person drink several glasses of water.
KEEP OUT OF REACH OF CHILDREN.

APPLICATION

To read about the method of application, refer to Finitec's "Method of application for floor finishes".

