

Technical data sheet

Finitec Recoater

PHYSICAL PROPERTIES

Color	White
Solid content (w/w)	25 % ± 1 %
pH	9,5 ± 0,2
Resistance to chemicals	Excellent
VOC	227 g/L
Flash point	N. A.
Luster 60°	Gloss: 75 % - Semi-gloss: 55 % - Satin: 25 %
Freeze / thaw stability	Keep from freezing
Drying time (depending on conditions)	To touch: 1 hour
	To recoat: 2 to 3 hours
	Light traffic: 4 hours
	Furniture: 24 hours
	Carpets and rugs: 10 days
	Complete cure: 10 days
Viscosity	23 to 25 seconds (Zahn #2)
Density	1,03 - 1,04 kg/L

TECHNICAL DATA

Coverage	165 sq.ft. (15,3 m ²) / liter (depending on conditions)
Available size	3,64 L
Shelflife	12 months (when kept in its original container)
Tools	Finitec applicator, T-bar, brush or 3/8" (10 mm) roller
Tools clean-up	Water
Storage	Between 10 and 30 °C (50 and 85 °F)
Waste disposal	Recycle if possible (Consult local authorities)



FIRST AID AND WARNING

In case of eye or skin contact, rinse well with water for 15 minutes. In case of inhalation, allow the victim to rest in a well-ventilated area. If swallowed, seek medical attention. Do not induce vomiting. Have conscious person drink several glasses of water. KEEP OUT OF REACH OF CHILDREN.

APPLICATION

To read about the method of application, refer to Finitec's "Method of application for floor finishes".