

### Technical data sheet

#### Furniture and Woodworks 6000

##### PHYSICAL PROPERTIES

Color	White
Solid content (w/w)	30 % ± 2 %
pH	8,4 ± 0,4
Resistance to chemicals	Excellent
Resistance to abrasion (Taber test)	Mass loss: 21 mg (1000 révolutions - ASTM D-4060)
VOC	269 g/L
Flash point	N. A.
Luster 60°	Semi-gloss: 55 % - Satin: 25 %
Freeze / thaw stability	Keep from freezing
Drying time (depending on conditions)	To touch: 1 hour
	To recoat: 2 to 3 hours
	Light contact: 4 hours
	First wet cleaning: 10 days Complete cure: 10 days
Viscosity	23 to 25 seconds (Zahn #2)
Density	1,04 - 1,05 kg/L

##### TECHNICAL DATA

Coverage	165 sq.ft. (15,3 m <sup>2</sup> ) / liter (depending on conditions)
Available size	1 L
Shelflife	12 months (when kept in its original container)
Tools	Finitec applicator, brush or spray gun
Tools clean-up	Water
Storage	Between 10 and 30 °C (50 and 85 °F)
Waste disposal	Recycle if possible (Consult local authorities)



#### FIRST AID AND WARNING

In case of eye or skin contact, rinse well with water for 15 minutes. In case of inhalation, allow the victim to rest in a well-ventilated area. If swallowed, seek medical attention. Do not induce vomiting. Have conscious person drink several glasses of water. **KEEP OUT OF REACH OF CHILDREN.**

#### APPLICATION

To read about the method of application, refer to Finitec's "Method of application for furniture and woodworks finishes".