

# TECHNICAL DATA SHEET

## DESCRIPTION

The AcoustiTECH VP membrane is suitable for all types of floated flooring installations. With a vapor barrier membrane integrated to the underlayment, it is a must have for your floated installation projects.

## COMPATIBILITY

### ADHESIVE

N/A

### FLOORING

Engineered floors  
Laminate



THERMAL COMFORT



ACOUSTIC COMFORT



MECHANICAL STRENGTH

# TECHNICAL DATA SHEET

## PERFORMANCE TABLE

Test	Suspended ceiling	Structure	Flooring type	Installation	Acoustic performance	Acoustic comfort
T.71.2	Yes	Concrete 8"	Engineered	Floated	AIIC: 72	A-HIIC: 84
T.8.10	No	Concrete 9"	Engineered	Floated	AIIC: 62	A-HIIC: 72
T.105.9	Yes	Hambro D500 + 4" concrete topping	Engineered	Floated	AIIC: 67	A-HIIC: 72
T.128	No	Wood + Gypcrete 1,5" + Insonomat + Insulation + Acoustivibe + gypsum board (2x)	Engineered	Floated	IIC: 63 STC:63	HIIC: 73
T.19	No	Concrete 8"	Laminate	Floated	AIIC: 60	A-HIIC: 67
T.118.10	No	Wood + Gypcrete 1,5" + Insulation + Gypsum board (2x)	Laminate	Floated	AIIC: 56	A-HIIC: 67

## PHYSICAL PROPERTIES

Type of fibre	Needle-punched polyester fibers
Type of film	Laminated polyester
VOC	0 g/L
Moisture	Rot-resitant
Flammability	1 (National Fire Protection Association. NFPA)
Length	10.2 m (33.3 ft)
Width	0.914 m (36 in)
Thickness	2.2 mm ± 10%
Weight	±6 lb (±2.7 kg)
Coverage	9.3 m <sup>2</sup> (100 ft <sup>2</sup> )

## TECHNICAL DATA

PERM (vapor barrier) ASTM E96	0.09
R factor ASTM C518	0.439
R factor of the assembly	0.439 to 0.878 without floor covering
Robinson ASTM C-267	N/A
Grab tensile strength CAN-148.1 - no 7.3	450 N ±5%
Grab tensile elongation CAN-148.1 - no 7.3	80% to 120%
"Mullen" bursting CAN-4.2 - no 11.1	1700 kPa ±5%
Trapazoidal tear CAN-4.2 - no 12.1	175 N ±5%
Reflectivity	10%

