

Instructions

Furniture and Woodworks

For new or restored wood (3-4 coats): apply on a dry clean bare wood. Make sure to properly neutralize the scouring solution (follow manufacturer's recommendations).

For finished wood, restoration (1-2 coats): it is important to remove completely all shine of the wood (top coat).

Appropriate for the majority of oil or water based finishes and stains. Application must be done at a room temperature between 21 and 25 °C (70 and 77 °F) and at a relative humidity of 45 %.

1- The surface needs to be prepared using a 120 grit sandpaper (DO NOT use steel wool) and remove dust. **2-** Proceed to an adherence, compatibility and color test by reproducing jobsite application conditions and methods. **3-** Method of application: **A)** Shake the finish vigorously for 45 seconds and let stand 10 minutes to allow bubbles to break. **B)** Spread a uniform coat following the wood grain using a brush, a foam brush or a finish applicator. **C)** Allow about 2 to 3 hours of drying between coats (may vary according to conditions). **D)** Sand between coats using a 180 grit sandpaper. **E)** It is not necessary to sand before the last coat if the time between applications does not exceed 3 hours.

Clean tools with water.

Shelflife: at least 12 months when kept in its original container. Keep from freezing.

Maintenance: wait 10 days before the first wet cleaning.

NOTE: Do not cover the surface before the finish is fully cured (10 days).

FIRST AID: In case of eye or skin contact, rinse well with water. In case of inhalation, allow the victim to rest in a well-ventilated area. If swallowed, seek medical attention. Do not induce vomiting.

KEEP OUT OF REACH OF CHILDREN.

WARRANTY: Finitec Hardwood Products Inc. certifies that the product is free from manufacturing defect. The user assumes all responsibility for use in accordance with instructions of this label. Manufacturer's responsibility is limited to replacement of the product.